

★ EUROBELT ★

C O N V E Y O R B E L T S



TECHNICAL DATA

CHEMICAL RESISTANCE

CHEMICAL RESISTANCE

CHEMICAL NAME	PP		PE		AC	
	20 °C	60 °C	20 °C	60 °C	20 °C	60 °C
Acetic acid	V	V	V	Q	-	-
Acetic acid (5%)	V	V	V	V	V	-
Acetone	V	V	V	V	Q	Q
Alcohol (all types)	V	V	V	V	-	-
Aluminium compounds	V	V	V	V	-	-
Alums (all types)	V	V	V	V	-	-
Ammonia	V	V	V	V	-	-
Ammonium compounds	V	V	V	V	-	-
Amyl acetate	Q	NV	Q	NV	-	-
Amyl chloride	NV	NV	Q	NV	-	-
Aniline	V	V	V	NV	-	Q
Aqua regia	NV	NV	Q	NV	-	-
Arsenic acid	V	V	V	V	-	-
Barium compounds	V	V	V	V	-	-
Barium soap fat	V	Q	-	-	-	-
Beer	V	V	V	V	-	-
Benzene	Q	NV	Q	NV	V	Q
Benzene sulphonic acid (10%)	V	V	V	V	-	-
Benzoic acid	V	V	V	V	-	-
Borax	V	V	V	V	-	-
Boric acid	V	V	V	V	-	-
Brake fluid	V	V	-	-	V	V
Brine (10%)	V	V	V	V	V	V
Bromic acid	NV	NV	NV	NV	-	-
Bromine, liquid or vapour	NV	NV	NV	NV	-	-
Bromine water	NV	NV	-	-	-	-
Butyl acetate	NV	NV	Q	NV	-	-
Butyl acid	NV	NV	V	Q	-	-
Butyric acid	V	-	V	Q	-	-
Calcium compounds	V	V	V	V	-	-
Calcium soap fat	V	Q	-	-	-	-

This chemical resistance guide is merely informative and it is based on specifications given by the suppliers of the technical plastics employed in our manufacturing process.

PP	Polypropylene
PE	Polyethylene
AC	Polyacetal
V	Valid
NV	Not Valid
Q	Questionable
-	No Information

CHEMICAL RESISTANCE

CHEMICAL NAME	PP		PE		AC	
	20 °C	60 °C	20 °C	60 °C	20 °C	60 °C
Calgonite (0,3%)	V	V	-	-	V	V
Carbon dioxide	V	V	V	V	-	-
Carbon disulphide	Q	NV	Q	NV	-	-
Carbon tetrachloride	NV	NV	NV	NV	V	Q
Cellosolve TM	V	V	-	-	-	-
Chloracetic acid	V	V	-	-	-	-
Chlorine-gas	NV	NV	Q	NV	NV	NV
Chlorine water (0,4% Cl)	V	Q	-	-	NV	NV
Chlorobenzene	NV	NV	Q	NV	-	-
Chloroform	NV	NV	NV	NV	-	-
Chlorosulphonic acid	NV	NV	NV	NV	-	-
Chlorox	NV	V	Q	-	-	NV
Chromic acid (50%)	V	V	V	Q	-	-
Citric acid	V	V	V	V	-	-
Citric acid (10%)	V	V	V	V	V	-
Citrics juice	V	V	V	V	-	-
Clorine liquid	NV	NV	NV	NV	NV	NV
Coconut oil	V	V	V	V	-	-
Copper compounds	V	V	V	V	-	-
Corn oil	V	V	V	V	-	-
Cottonseed oil	V	V	V	V	-	-
Cresol	V	V	V	Q	-	-
Cyclohexane	V	Q	NV	NV	-	-
Cyclohexanone	V	Q	NV	NV	-	-
Detergents	V	V	V	V	V	V
Dextrine	V	V	V	V	-	-
Di-iso-octyl phthalate	V	V	-	-	-	-
Dibutyl phthalate	V	Q	-	-	-	-
Diethanolamine	V	V	-	NV	-	-
Diethyl ether	NV	NV	NV	NV	Q	Q
Diglycolic acid (30%)	V	V	V	V	-	-
Dimethyl phthalate	V	V	-	-	-	-

This chemical resistance guide is merely informative and it is based on specifications given by the suppliers of the technical plastics employed in our manufacturing process.

PP	Polypropylene
PE	Polyethylene
AC	Polyacetal
V	Valid
NV	Not Valid
Q	Questionable
-	No Information

CHEMICAL RESISTANCE

CHEMICAL NAME	PP		PE		AC	
	20 °C	60 °C	20 °C	60 °C	20 °C	60 °C
Dimethylamine	V	-	-	-	-	-
Diocetyl phthalate	V	Q	-	-	-	-
Ethyl acetate	V	V	Q	Q	Q	NV
Ethyl ether	Q	Q	-	-	-	-
Ethylamine	V	V	-	-	-	-
Ethylene chloride	NV	NV	-	-	-	-
Ethylene glicol (50%)	V	V	V	V	V	Q
Ferric/ferrous compounds	V	V	V	V	-	-
Formaldehyde (37%)	V	V	V	Q	-	-
Formic acid (85%)	V	Q	V	V	-	-
Freon	-	-	V	V	Q	Q
Fuel oil	V	Q	V	NV	Q	Q
Furfural	NV	NV	Q	NV	-	-
Glucose	V	V	V	V	-	-
Glycerol	V	V	-	-	-	-
Grease	V	V	V	Q	-	-
Heptane	NV	NV	Q	NV	V	V
Hexane	V	Q	NV	NV	-	-
Hydriodic acid	NV	NV	-	-	-	-
Hydrobromic acid (50%)	V	V	V	V	-	-
Hydrochloric acid	V	V	V	V	NV	NV
Hydrochloric acid (10%)	V	V	V	V	NV	NV
Hydrofluoric acid (35%)	V	V	V	V	NV	NV
Hydrogen peroxide (3%)	V	V	V	V	V	V
Hydrogen peroxide (90%)	Q	Q	V	Q	-	-
Hydrogen sulphide	V	V	V	V	-	-
Igepal (50%)	V	V	-	-	V	Q
Iodine-glasses	V	V	Q	Q	-	-
Isooctane	NV	NV	V	-	-	-
Kerosine	Q	NV	Q	Q	V	V
Lactic acid	V	V	V	V	-	-

This chemical resistance guide is merely informative and it is based on specifications given by the suppliers of the technical plastics employed in our manufacturing process.

PP	Polypropylene
PE	Polyethylene
AC	Polyacetal
V	Valid
NV	Not Valid
Q	Questionable
-	No Information

CHEMICAL RESISTANCE

CHEMICAL NAME	PP		PE		AC	
	20 °C	60 °C	20 °C	60 °C	20 °C	60 °C
Lanolin	V	Q	V	V	-	-
Lard	-	-	V	V	-	-
Lauric acid	V	V	V	V	-	-
Lead acetate	V	V	V	V	-	-
Ligroine	Q	NV	-	-	-	-
Lime sulfur	V	-	-	-	-	-
Linseed oil	V	V	V	V	V	V
Lubricating oil	V	Q	-	-	V	V
Magnesium compounds	V	V	V	V	-	-
Malic acid (50%)	V	V	V	V	-	-
Manganese sulphate	V	-	V	V	-	-
Margarine	V	V	V	V	-	-
Mercury	V	V	V	V	-	-
Mercury compounds	V	V	V	V	-	-
Methyl cellosolve	V	-	-	-	-	-
Methyl chloride	NV	NV	-	-	-	-
Methyl ethyl kesone	V	Q	NV	NV	-	-
Methyl sulphuric acid	V	V	V	V	-	-
Methylene chloride	Q	NV	NV	NV	-	-
Mineral oil	Q	NV	V	NV	V	V
Mineral alcohols	Q	NV	-	-	-	-
Molasses	V	V	V	V	-	-
Motor oil	V	Q	-	-	V	V
Naphtha	V	Q	Q	NV	-	-
Nickel compounds	V	V	V	V	-	-
Nitric acid (30%)	V	Q	V	V	NV	NV
Nitric acid (50%)	Q	NV	V	Q	NV	NV
Nitric acid (fuming)	NV	NV	NV	NV	NV	NV
Nitrobenzene	V	Q	NV	NV	-	-
Nitrous acids	Q	NV	-	-	-	-
Nitrous oxide	V	-	-	-	-	-

This chemical resistance guide is merely informative and it is based on specifications given by the suppliers of the technical plastics employed in our manufacturing process.

PP	Polypropylene
PE	Polyethylene
AC	Polyacetal
V	Valid
NV	Not Valid
Q	Questionable
-	No Information

CHEMICAL RESISTANCE

CHEMICAL NAME	PP		PE		AC	
	20 °C	60 °C	20 °C	60 °C	20 °C	60 °C
Oil for transformers	V	Q	V	Q	-	-
Oleic acid	V	NV	-	-	V	V
Olive oil	V	V	V	V	-	-
Oxalic acid	V	V	V	V	-	-
Oxygen	NV	NV	-	-	-	-
Ozone	NV	NV	Q	NV	-	-
Palmitic acid (70%)	V	V	V	V	-	-
Perchloric acid (20%)	V	V	V	V	-	-
Perchloroethylene	NV	NV	NV	NV	-	-
Petrol	Q	NV	V	NV	V	V
Phenol (5%)	V	V	V	V	NV	NV
Phenol	V	V	V	V	NV	NV
Phosphoric acid (30%)	V	V	V	V	-	-
Phosphoric acid (85%)	V	V	V	V	-	-
Photographic solutions	V	V	V	V	-	-
Phthalic acid (50%)	V	V	V	V	-	-
Plating solutions	V	V	V	V	-	-
Potassium compounds	V	V	V	V	-	-
Potassium iodide 3% iodine	V	V	V	V	-	-
Potassium hydroxide	V	V	V	V	-	-
Potassium permanganate	V	Q	V	V	-	-
Silver cyanide	V	V	-	-	-	-
Silver nitrate	V	V	V	V	-	-
Sodium chlorite	V	Q	V	V	-	-
Sodium compounds	V	V	V	V	-	-
Sodium hydroxide	V	V	V	V	-	-
Sodium hydroxide (60%)	V	V	V	V	V	V
Sodium hypochlorite (5% Cl.)	V	Q	-	-	NV	NV
Stannic chloride	V	V	V	V	-	-
Stannous chloride	V	V	V	V	-	-
Stearic acid	V	Q	V	V	-	-

This chemical resistance guide is merely informative and it is based on specifications given by the suppliers of the technical plastics employed in our manufacturing process.

PP	Polypropylene
PE	Polyethylene
AC	Polyacetal
V	Valid
NV	Not Valid
Q	Questionable
-	No Information